

DURACOLOR® / COLORPLANK®

SUMMARY TECHNICAL INFORMATION SHEET

Range of section shapes	CLASSIC or TRADITIONAL	COLONIAL
Composition	40 to 45% cement, 45 to 50% silica, 8 to 10% cellulose fibres, 3 to 6% tow	
Board	Single board	Board with groove on top part
Appearance	Wood textured	
Paint finish	Acrylic primer on all the faces Acrylic paint on the visible faces	
Colours	12 Standard colours Colours made as requested depending on quantities	
Dimensions	Length 3657 mm Width 210 mm, effective width 180 mm Thickness 8 mm	
Installation	By overlap horizontally and vertically	By overlap horizontally
Fixing	By nailing or screwing every 600 mm (horizontal installation) or 400 mm (vertical installation) on timber framing element; by hidden screwing every 600 mm (horizontal installation) on metal framing element	
Effective surface per board	0.66 m ²	
Effective surface per pallet	230 boards = 151.5 m ²	
Weight per surface area	12.6 kg/m ²	
Density	1350 kg/m ³	
Guarantee and certifications	<p>Ten year guarantee SMABTP no. 285425V Fire reaction rating M1 no. D040541-CEMAT/1 Fire rating A2-s1, d0 no. RA04-0153 according to European Standard NF EN 13501-1</p> <p>CSTB Technical Assessment no. 2/08-1310 ReVETIR rating r2e2V3E3T2I1R4 (horizontal installation) and r2e2V1E3T3I1R4 (vertical installation) Absence of asbestos – Report no. 99/312</p>	
Strength in resistance tests	CSTB tests for resistance to the effects of wind and outside impacts	
Servicing	Servicing strictly minimised, using water and a non-abrasive detergent. Clean very dirty surfaces with a soft nylon brush and a water hose at a pressure less than 3 bars.	